Kimio KAWAGOE et al.

Docket No. 020402

REMARKS

The above amendment is believed to place the claims in proper condition for examination.

Early and favorable action is awaited.

Attached hereto is a marked-up version of the changes made to the specification and claims by the current amendment. The attached page is captioned "Version with markings to show changes made."

In the event there are any additional fees required, please charge our Deposit Account No. 01-2340.

Respectfully submitted,

Stephen G. Adrian

Reg. No. 32,878

ARMSTRONG, WESTERMAN & HATTORI, LLP

Atty. Docket No. 020402

Suite 1000

1725 K Street, N.W.

Washington, D.C. 20006

Tel: (202) 659-2930

SGA/yap

Kimio KAWAGOE et al.

Docket No. 020402

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE SPECIFICATION:

Te paragraph beginning at page 2, line 18, has been amended as follows:

That is, the present invention is related to a sliding bearing, wherein an overlay, which consists of at least one solid lubricant and a binder resin, covers an aluminum-alloy bearing layer bonded on the backing metal, characterized in that said overlay consists of an upper layer, which contains the solid lubricant essentially consisting of MoS₂, and a <u>lower</u> layer consisting of one or both of at least one solid lubricant and at least one hard additive (hereinafter referred to as "the additive"), and, further, the MoS₂ gradually decreases without steps and the hard additive increases gradually in the direction from the top layer to the bottom layer. The present invention is hereinafter described in detail.

IN THE CLAIMS:

Claims 8 and 9 have been amended as follows:

8. (Amended) A sliding bearing according to any one of claims 1 through [7] 6, wherein said upper layer [consist] consists of two or more sub-layers having different MoS₂ content, the MoS₂ content of the upper sub-layer is more than the MoS₂ content of the lower sub-layer.

Kimio KAWAGOE et al.

Docket No. 020402

9. (Amended) A sliding bearing according to any one of claims 1 through [8] 6, wherein said lower layer consists of two or more sub-layers having different additive amount.